

**IN THE CLAIMS:**

Kindly amend claims 9 and 10 as follows.

CLAIM SUMMARY DOCUMENT

B<sup>1</sup>  
Claim 1 (Original) A perpendicular magnetic recording medium in which a perpendicular magnetic enhancement layer having a thickness of 15 nm or greater is deposited between a substrate and a perpendicular magnetic recording layer.

Claim 2 (Original) The perpendicular magnetic recording medium of claim 1, further comprising a perpendicular orientation promoting underlayer between the substrate and the perpendicular magnetic enhancement layer for promoting the perpendicular orientation of the perpendicular magnetic recording layer.

Claim 3 (Previously Amended) The perpendicular magnetic recording medium of claim 1, wherein the perpendicular magnetic enhancement layer is formed of at least one selected from the group consisting of Pt, Au, Pd and an alloy of these materials.

Claim 4 (Original) The perpendicular magnetic recording medium of claim 2, wherein the perpendicular orientation promoting underlayer is formed of Ti or a Ti alloy and has a thickness less than 10 nm.

Claim 5 (Previously Amended) The perpendicular magnetic recording medium of claim 1, wherein the perpendicular magnetic recording layer is of a CoCr alloy.

Claim 6 (Original) The perpendicular magnetic recording medium of claim 5, wherein the perpendicular magnetic recording layer further comprises at least one material selected from the group consisting of B, Pt, Ta, V, Nb, Zr, Y, and Mo.

B  
Claim 7 (Previously Amended) The perpendicular magnetic recording medium of claim 1, further comprising a protective layer and a lubricant layer sequentially on the perpendicular magnetic recording layer.

Claim 8 (Previously Amended) The perpendicular magnetic recording medium of claim 1, wherein perpendicular magnetic enhancement layer is formed of Pt and has a thickness no less than 15 nm.

Claim 9 (Currently Amended) The perpendicular magnetic recording medium of claim 1, further comprising a perpendicular orientation promoting underlayer, wherein the perpendicular magnetic recording medium has a double-layer structure including a soft magnetic layer between the substrate and the perpendicular orientation promoting underlayer.

10. (Currently Amended) The perpendicular magnetic recording medium of claim 1, further comprising a perpendicular orientation promoting underlayer, wherein the perpendicular magnetic recording medium has a pseudo double-layer structure including a

soft magnetic layer between the perpendicular orientation promoting underlayer and the perpendicular magnetic recording layer.

B  
Claim 11 (Previously Added) The perpendicular magnetic recording medium of claim 2, wherein the perpendicular magnetic enhancement layer is formed of at least one selected from the group consisting of Pt, Au, Pd and an alloy of these materials.

Claim 12 (Previously Added) The perpendicular magnetic recording medium of claim 2, wherein the perpendicular magnetic recording layer is formed of a CoCr alloy.

Claim 13 (Previously Added) The perpendicular magnetic recording medium of claim 2, further comprising a protective layer and a lubricant layer sequentially on the perpendicular magnetic recording layer.

Claim 14 (Previously Added) The perpendicular magnetic recording medium of claim 2, wherein perpendicular magnetic enhancement layer is formed of Pt and has a thickness no less than 15 nm.

Claim 15 (Previously Added) The perpendicular magnetic recording medium of claim 2, wherein the perpendicular magnetic recording medium has a double-layer structure including a soft magnetic layer between the substrate and the perpendicular orientation promoting underlayer.

*B1  
cancel*  
Claim 16 (Previously Added) The perpendicular magnetic recording medium  
of claim 2, wherein the perpendicular magnetic recording medium has a pseudo double-  
layer structure including a soft magnetic layer between the perpendicular orientation  
promoting underlayer and the perpendicular magnetic recording layer. . .

---